

GLOBALPRENE 7550U Styrene-Ethylene/Butylene block copolymer 苯乙烯-乙烯/丁烯嵌段共聚物

Features 特性：		Typical Application 一般應用：		
• Linear and clear block copolymer	線型透明嵌段共聚物	• Plastic modification	塑料改質	
• Excellent weather and heat resistance	優良的耐候性及耐熱性	• Adhesives	黏著劑	
• High mechanical strength	高機械強度	• Compounding for modification	混鍊改質	
• Good compatibility with plastics	與塑膠有好的相容性	• Toys	玩具	
		• Asphalt modification	瀝青改質	
Typical Properties：		Test Method	Unit	Value
一般性質		測試方法	單位	數值
SM Content 苯乙烯含量		ASTM D5775	%	30
Specific Gravity 比重		ASTM D792	g/cc	0.91
Volatile Matter 揮發份		ASTM D5668	%	0.2
Ash Content 灰份		ASTM D5667	%	0.05
20wt% / 25°C Toluene Viscosity 20wt% / 25°C 甲苯黏度		ASTM D2196	cP	1850
				1300~2400

Note : SM content is measured on polymer before hydrogenation. 苯乙烯含量為氫化前測量值

Packing 包裝：13kg PE bag 13 公斤 PE 袋

All ingredients in the products are in compliance with the following chemical inventories：

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECIS)

符合美國食品及藥物管理局 21 CFR 177.1810(b)(3)之規範

Comply with FDA CFR 177.1810(b)(3)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

商務服務處

Sales Services

台灣 台北市松山區八德路四段 85 號 3 樓

3F., No.85, Sec. 4, Bade Rd., Songshan Dist., Taipei City 105, Taiwan

Tel：+886-2-27631611

Fax：+886-2-27482661

環球橡膠股份有限公司

LCY GRIT CORP.

台灣 高雄市小港區中林路 16 號

No.16, Zhonglin Rd., Xiaogang Dist., Kaohsiung City 812, Taiwan

Tel：+886-7-8712268

Fax：+886-7-8712296

惠州李長榮橡膠有限公司

中國 廣東省惠州市大亞灣經濟技術開發區石化區石化大道中 299 號

No.299 Shihua Dadaozhong, Dayawan Economic & Technological Development Zone, Huizhou, Guangdong, 516082, P.R.C.

Tel：+86-752-5599000

Fax：+86-752-5599002