

Infino AE-3063I

Lotte Chemical Corporation - Polycarbonate + PBT

Tuesday, June 27, 2023

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Automotive Applications		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.20	g/cm ³	ASTM D792
Density (Natural)	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	45	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	45	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Molding Shrinkage - Across Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	0.50 to 0.80	%	
Flow : 2.00 mm	0.50 to 0.80	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	1720	MPa	ASTM D638
Tensile Modulus	1600	MPa	ISO 527-1/50
Tensile Strength ² (Yield)	49.0	MPa	ASTM D638
Tensile Stress (Yield)	50.0	MPa	ISO 527-2/50
Tensile Strength ² (Break)	47.1	MPa	ASTM D638
Tensile Stress (Break)	48.0	MPa	ISO 527-2/50
Tensile Elongation ² (Break)	120	%	ASTM D638
Tensile Strain (Break)	120	%	ISO 527-2/50
Flexural Modulus ³	1860	MPa	ASTM D790
Flexural Modulus ⁴	1800	MPa	ISO 178
Flexural Strength ³	68.6	MPa	ASTM D790
Flexural Stress ⁴	67.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (23°C)	54	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
-30°C, 6.35 mm	370	J/m	
23°C, 3.18 mm	760	J/m	
23°C, 6.35 mm	640	J/m	
Notched Izod Impact Strength ⁵ (23°C)	52	kJ/m ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Rockwell Hardness (R-Scale)	110		ISO 2039-2

Infino AE-3063I

Lotte Chemical Corporation - Polycarbonate + PBT

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed, 6.40 mm	92.0	°C	ASTM D648
Deflection Temperature Under Load 1.8 MPa, Unannealed, 4.00 mm	78.0	°C	ISO 75-2/A
Vicat Softening Temperature	120	°C	ISO 306/B50

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	100	°C
Hot Air Dryer	110	°C
Drying Time		
Desiccant Dryer	4.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	230 to 240	°C
Middle Temperature	240 to 250	°C
Front Temperature	250 to 260	°C
Nozzle Temperature	260	°C
Mold Temperature	40 to 60	°C
Injection Pressure	49.0 to 245	MPa
Back Pressure	0.490 to 1.96	MPa
Screw Speed	50 to 150	rpm

Injection Notes

Hot Runner Temperature: 260°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 2.8 mm/min

⁴ 2.0 mm/min

⁵ 4mm