

Infino GC-1033

Lotte Chemical Corporation - Polycarbonate + ABS

Saturday, July 1, 2023

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.19	g/cm ³	ASTM D792
Density (Natural)	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	35	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	35	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Molding Shrinkage - Across Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	0.40 to 0.70	%	
Flow : 2.00 mm	0.40 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	2260	MPa	ASTM D638
Tensile Modulus	2300	MPa	ISO 527-1/50
Tensile Strength ² (Yield)	57.9	MPa	ASTM D638
Tensile Stress (Yield)	59.0	MPa	ISO 527-2/50
Tensile Strength ² (Break)	58.8	MPa	ASTM D638
Tensile Stress (Break)	60.0	MPa	ISO 527-2/50
Tensile Elongation ² (Break)	30	%	ASTM D638
Tensile Strain (Break)	30	%	ISO 527-2/50
Flexural Modulus ³	2330	MPa	ASTM D790
Flexural Modulus ⁴	2400	MPa	ISO 178
Flexural Strength ³	87.3	MPa	ASTM D790
Flexural Stress ⁴	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁵ (23°C)	30	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
23°C, 3.18 mm	640	J/m	
23°C, 6.35 mm	150	J/m	
Notched Izod Impact Strength ⁵ (23°C)	50	kJ/m ²	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Rockwell Hardness (R-Scale)	119		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 6.40 mm	92.0	°C	

Infino GC-1033

Lotte Chemical Corporation - Polycarbonate + ABS

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed, 4.00 mm	86.0	°C	ISO 75-2/A
Vicat Softening Temperature	107	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 to 3.0 mm)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	80	°C
Hot Air Dryer	80	°C
Drying Time		
Desiccant Dryer	3.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	0.040	%
Rear Temperature	230 to 250	°C
Middle Temperature	240 to 260	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	260	°C
Mold Temperature	60 to 90	°C
Injection Pressure	9.81	MPa
Back Pressure	0.490 to 2.94	MPa
Screw Speed	20 to 200	rpm

Injection Notes

Hot Runner Temperature: 250 to 270°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 2.8 mm/min

⁴ 2.0 mm/min

⁵ 4mm