

TYPICAL DATA SHEET*	ISSUE DATE	Feb-2022	
POLYETHYLENE	<u>WWW.TPCO.IR</u>		
LL0220KJ	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612		

LL0220KJ is linear low density polyethylene copolymer containing butene-1(C4) as co monomer. It is suitable for blending with conventional LDPE for blown film applications. Film made from pure LL0220KJ has the following advantages over LDPE: good balance of mechanical properties, good optical properties and easy opening properties in 2-layer film. This grade has food contact approval.

Applications: light and medium duty films with good optical properties.

PROPERTY		UNIT	TEST METHOD	TYPICAL VALUE
	140)	//	10TUD (600	
MELT FLOW INDEX (190°C 2.16 MFR (UNDER LOAD 21.6KG/2.16		g/10min	ASTM D-1238	2.4 29-30
DENSITY	iko)	gr/cm3	ASTM D-1505	0.921
VICAT SOFTENING POINT		°C	ASTM D-1525	100
FILM**				
DART DROP IMPACT	METHOD	GR	ASTM D-1709	90
	Α		<u> </u>	
TENSILE STRESS AT YEILD	MD/TD	MPA 🦯	ASTM D-882	10/11
TENSILE STRESS AT BREAK	MD/TD	MPA	ASTM D-882	30/25
TEAR STRENGTH	MD/TD	gr/25µ	ASTM D1922	100/300
1%SECANT MODULUS	MD/TD	MPA	ISO 1184	80/100
ELONGATION AT BREAK	MD/TD	%	ASTM D-882	1000/1100
WHITENESS INDEX	-	%	ASTM E-313	50
GLOSS (45°)	4	%°	ASTM D-2457	30

^{*}All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (Standard Sales Specifications)

^{**38}µm blown film with blow up ratio 2:1,225°c melt temperature. MD: Machine Direction, TD: Transverse Direction Grade Suffix (Additives Indication) KJ: GENERAL ANTIOXIDANT WITH SLIP AGENT/ANTIBLOCKING AGENTS